



Technical Data Sheet

Revolution® (R122) Machine Film

Ultra performance co-extruded cast machine grade stretch wrap film

PROPERTY	UNITS		TEST METHOD	TYPICAL RESULT
Thickness	Mil (Micron)		ASTM D4649	0.51 (13.0)
Color				Clear
Haze	%		ASTM D1003	<2.0
Gloss	In	% @45°	ASTM D2457	75.0
	Out			79.0
Dart Impact Strength	g		ASTM D1709	250
Tensile Strength at Break	MD	psi	ASTM D882	5,550
	TD			4,550
Tensile Strength at 200%	MD	psi	ASTM D882	2,070
	TD			1,370
Elongation at Break	MD	%	ASTM D882	475
	TD			660
Elmendorf Tear Strength	MD	g	ASTM D1922	145
	TD			450

Berry Plastics Corporation
Corporate Office
101 Oakley Street
Evansville, IN 47710
CS 1.866.787.3456
Fax 1.866.787.3457
www.berryplastics.com

This material is a proprietary blend of various polymer resins. The properties listed above are typical values and not intended for use as limiting specifications. No representation, warranty or guarantee is made as to the Technical Data Sheet's accuracy or completeness. This information is subject to change at any time. It is the responsibility of the user to test this product for its application to determine if it meets user's performance requirements. Neither Berry Plastics nor its affiliates is liable for any loss or damage that may occur from the use of this information.

Rev 1B_0817