



**Product Data Sheet
VMAXX**

| Property | ASTM Method | Value | Value | Value | Value | Value |
|------------------------|-------------|------------------|------------------|------------------|------------------|------------------|
| | | Ultra Light | Light | Medium | Heavy | 80 |
| Thickness (Mil) | | 0.260 | 0.290 | 0.320 | 0.360 | 0.430 |
| Haze | % | 1.9 | 2.0 | 2.2 | 2.3 | 2.4 |
| Cling | D-5458 | 115 min, 125 tgt | 115 min, 125 tgt | 115 min, 125 tgt | 115 min, 125 tgt | 115 min, 125 tgt |
| | | | | | | |
| Elongation % (MD) | D-882 | 65% | 70% | 115% | 125% | 130% |
| Elongation % (TD) | D-882 | 745% | 785% | 805% | 815% | 825% |
| Tensile Ultimate (MD) | D-882 | 13,000 PSI | 14,100 PSI | 15,200 PSI | 15,875 PSI | 16,500 PSI |
| Tensile Ultimate (TD) | D-882 | 3,300 PSI | 3,500 PSI | 3,300 PSI | 3,500 PSI | 3,750 PSI |
| Dart Drop (Gram/sheet) | D-1709 | 120 | 130 | 160 | 175 | 195 |

NOTE: The data presented above are nominal values for the product type described and must not be construed as specifications. Therefore no guaranty expressed or implied.

Manufacturing process for pre-stretch has a +/- variance of 5%